

# **WHITTINGTON'S DICTIONARY OF PLASTICS**

*by*

**Lloyd R. Whittington**



**Sponsored by the  
SOCIETY OF PLASTICS ENGINEERS, INC.**



**LANCASTER • BASEL**

*Published in the Western Hemisphere by*  
Technomic Publishing Company, Inc.  
851 New Holland Avenue  
Box 3535  
Lancaster, Pennsylvania 17604 U.S.A.

*Distributed in the Rest of the World by*  
Technomic Publishing AG

©1978 by Technomic Publishing Company, Inc.  
All rights reserved

No part of this publication may be reproduced, stored in a retrieval system, or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of the publisher.

Printed in the United States of America  
10 9 8 7 6 5 4

Main entry under title:  
Whittington's Dictionary of Plastics

A Technomic Publishing Company book  
Bibliography: p.

Library of Congress Card No. 78-73776  
ISBN No. 0-87762-267-1

bis(Alkylthio) Cadmium. A stabilizer for PVC.

Allobar. A form of an element having different atomic weights and thus differing in isotropic composition from the naturally occurring form of the element.

Allomerism. A similarity of crystalline form with a difference in chemical composition. See POLYALLOMERS.

Allophanamide. See BIURET.

Allotrophy. The ability of a substance to exist in two or more solid, liquid or gaseous forms due to differences in the arrangement of atoms or molecules.

Alloy. A term sometimes used in the plastics industry to denote blends of polymers or copolymers with other polymers or elastomers. An example is a blend of styrene-acrylonitrile copolymer with butadiene-acrylonitrile rubber. The term *polyblend* is sometimes used for such mixtures.

Allyl. (n) The unsaturated radical  $C_3H_5$ , which upon liberation forms diallyl,  $C_6H_{10}$ , a pungent volatile liquid.

Allyl Alcohol.  $CH_2=CHCH_2OH$ . (propenyl alcohol, AA, 2-propen-1-ol). A colorless liquid with a characteristic pungent odor, obtained from the hydrolysis of allyl chloride (from propylene) with dilute caustic, or by the dehydration of propylene alcohol. It is a basic material for all allyl resins, and its esters are used as plasticizers.

Allyl Aldehyde. See ACROLEIN.

Allyl Chloride.  $CH_2=CHCH_2Cl$ . (3-chloropropene, alpha-chloropropylene, AC, chloroallylene) Used in the preparation of allyl alcohol and various thermosetting resins.

Allyl Cyanide.  $CH_2=CHCH_2CN$  (3-butenenitrile, vinyl-acetonitrile). Used as a crosslinking agent.

Allyl Diglycol Carbonate. (ADC) A colorless, water-clear monomer which can be polymerized and cast into a variety of transparent, optical grade products. The thermosetting polymer has the highest scratch and abrasion resistance of all transparent plastics. It can be copolymerized with other unsaturated monomers such as vinyl acetate or methyl methacrylate to produce polymers with a wide variety of properties.

Allyl Diglycol Carbonate Resins. Thermosetting resins with outstanding optical clarity, good abrasion resistance and mechanical properties. The resins are made by polymerizing the monomer of the same name with catalysts such as benzoyl peroxide or, preferably, diisopropyl peroxy dicarbonate. The monomer may also be copolymerized with a variety of monomers and unsaturated compounds such as vinyl acetate, methylmethacrylate and maleic anhydride to yield copolymers with a wide range of properties.

Allyl Esters. Esters of allyl alcohol, used in the production of plasticizers and resins.

# Plastics Technology Handbook

**Manas Chanda**

Department of Chemical Engineering  
Indian Institute of Science  
Bangalore, India

**Salil K. Roy**

Department of Mechanical and Production Engineering  
University of Singapore  
Singapore

**MARCEL DEKKER, INC.**

**New York and Basel**

Library of Congress Cataloging-in-Publication Data

Chanda, Manas  
Plastics Technology Handbook.

(Plastics engineering ; 12)

Bibliography: p.

Includes index.

1. Plastics. I Roy, S. K. (Salil K.),

II. Title. III. Series: Plastics engineering (Marcel Dekker, Inc.) ; 12.

TA455.P5C46 1986 620.1'923 86-19730

ISBN 0-8247-7564-3

COPYRIGHT © 1987 by MARCEL DEKKER, INC. ALL RIGHTS RESERVED

Neither this book nor any part may be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopying, microfilming, and recording, or by any information storage and retrieval system, without permission in writing from the publisher.

MARCEL DEKKER, INC.  
270 Madison Avenue, New York, New York 10016

Current printing (last digit):  
10 9 8 7 6 5 4 3 2 1

PRINTED IN THE UNITED STATES OF AMERICA




FIG. 1.4 Copolymer arrangements: (a) Two different types of mers (denoted by open and filled circles) are randomly placed. (b) The mers are alternately arranged. (c) A block copolymer. (d) A graft copolymer.

AAAAAAAAAAAAAAAAA  
B  
B  
B  
B  
B

Copolymerization, which may be compared to alloying in metallurgy, is very useful for synthesizing polymers with the required combination of properties. For example, polystyrene is brittle, and polybutadiene is flexible; therefore copolymers of styrene and butadiene should be more flexible than polystyrene but tougher than polybutadiene. The general-purpose rubber GRS (or SBR), the first practical synthetic rubber, is a copolymer of styrene and butadiene.